



**Boral Construction Materials
Materials Technical Services**
Unit 4, 3-5 Gibbon Road
Baulkham Hills NSW 2153 Australia
PO Box 400, Winston Hills NSW 2153
T: +61 2 9624 9900
F: +61 2 9624 9999
www.boral.com.au

TEST REPORT

Req No: 57461
File No: 258/14

Laboratory Sample No: 153838

Job description: CURING COMPOUND EVALUATION
Test Method: AS 3799 - 1998

CLIENT: EVENRANGE PTY LTD

Sample identification: Evencure BCP
Sample Description: Emulsified hybrid of petroleum and hydrocarbon resin curing compound.
Classification: Type 3, Class Z

Source of sample: supplied by client
Date of sampling: April 2014

Date of test: 12.05.2014

Method of application: by spraying at standard application rate of 5m²/L


TEST RESULTS:

Standard property, Test (Method)	Specification	Result	
Water retention efficiency AS 3799.3.1.2 (Method AS 3799 Appendix B)	Min. 90%	97%	NATA accreditation does not cover performance of these tests
Non - volatile content AS 3799.3.1.8 (Method AS 1580.301.1/ RTA T865)	N / A	54.4%	
Density AS 3799.3.1.9 (Method AS 1580.2002.1)	N / A	1.00	
Viscosity AS 3799.3.1.5 (Method AS 1580.214.5)	Min. 0.05 Pa's	0.11Pa's	
Drying Time AS 3799.3.1.4 (Method AS 1160 Appendix C)	Max. 4 hrs	4 hrs	
Stability of emulsion T 862 (RTA 3203)	Max 4%	0.5%	
Infrared absorption spectrum AS 3799.3.2 (Boral Method)	N / A	attached	
Residue 150µm AS 3799.3.1.6 (Method AS/NZS 2341.20)	Max. 0.2%	0.1%	

The sample submitted and identified by the client.

Shane Latham, File res, File

V.Mukhin

Approved Signatory 
Date 3.06.2014 Serial No. 125981

*This document is issued in accordance with the NATA's accreditation requirements.
Accredited for compliance with ISO/IEC 17025*

NATA Accredited Laboratory
Number: 547



ACCREDITED FOR
**TECHNICAL
COMPETENCE**