



**Boral Construction Materials**  
**Materials Technical Services**  
 Unit 4, 3-5 Gibbon Road  
 Baulkham Hills NSW 2153 Australia  
 PO Box 400, Winston Hills NSW 2153  
 T: +61 2 9624 9900  
 F: +61 2 9624 9999  
 www.boral.com.au

## TEST REPORT

**Req No: 57461**  
**File No: 258/14**

**Laboratory Sample No: 153838**

**Job description:** CURING COMPOUND EVALUATION  
**Test Method:** AS 3799 - 1998

**CLIENT: EVENRANGE PTY LTD**

**Sample identification:** Evencure BCP  
**Sample Description:** Emulsified hybrid of petroleum and hydrocarbon resin curing compound.  
**Classification:** Type 3, Class Z

**Source of sample:** supplied by client  
**Date of sampling:** April 2014

**Date of test: 12.05.2014**

**Method of application:** by spraying at standard application rate of 5m<sup>2</sup>/L


### TEST RESULTS:

Standard property, Test (Method)	Specification	Result	
<b>Water retention efficiency</b> AS 3799.3.1.2 (Method AS 3799 Appendix B)	Min. 90%	97%	NATA accreditation does not cover performance of these tests
<b>Non - volatile content</b> AS 3799.3.1.8 (Method AS 1580.301.1/ RTA T865)	N / A	54.4%	
<b>Density</b> AS 3799.3.1.9 (Method AS 1580.2002.1)	N / A	1.00	
<b>Viscosity</b> AS 3799.3.1.5 (Method AS 1580.214.5)	Min. 0.05 Pa's	0.11Pa's	
<b>Drying Time</b> AS 3799.3.1.4 (Method AS 1160 Appendix C)	Max. 4 hrs	4 hrs	
<b>Stability of emulsion</b> T 862 (RTA 3203)	Max 4%	0.5%	
<b>Infrared absorption spectrum</b> AS 3799.3.2 (Boral Method)	N / A	attached	
<b>Residue 150µm</b> AS 3799.3.1.6 (Method AS/NZS 2341.20)	Max. 0.2%	0.1%	

The sample submitted and identified by the client.

Shane Latham, File res, File

V.Mukhin

Approved Signatory   
 Date 3.06.2014 Serial No. 125981

This document is issued in accordance with the NATA's accreditation requirements.  
 Accredited for compliance with ISO/IEC 17025

NATA Accredited Laboratory  
 Number: 547



ACCREDITED FOR  
**TECHNICAL  
 COMPETENCE**