

TEST REPORT

File No: 258/10

Laboratory Sample No: 109950

Job description: CURING COMPOUND EVALUATION
Test Method: AS 3799 - 1998

CLIENT: EVENRANGE PTY LTD

Sample identification: Evencure W 30
Distributor: Evenrange Pty Ltd
Sample Description: Wax emulsion curing compound
Classification: Type 2, Class A

Source of sample: supplied by client
Date of sampling: 30.09.2010

Date of test: 26.10.2010

Method of application: by spraying at standard application rate of 5m²/L

TEST RESULTS:

Standard property, Test (Method)	Specification	Result	
Water retention efficiency AS 3799.3.1.2 (Method AS 3799 Appendix B)	Min. 90%	90%	
Non - volatile content AS 3799.3.1.8 (Method AS 1580.301.1/ RTA T865)	N / A	31.060%	NATA accreditation does not cover performance of these tests
Density AS 3799.3.1.9 (Method AS 1580.2002.1)	N / A	0.995	
Viscosity AS 3799.3.1.5 (Method AS 1580.214.5)	Min. 0.05 Pa's	0.05Pa's	
Drying Time AS 3799.3.1.4 (Method AS 1160 Appendix C)	Max. 4 hrs	3 hrs	
Stability of emulsion T 862 (RTA 3203)	Max 4%	3%	
Infrared absorption spectrum AS 3799.3.2 (Boral Method)	N / A	attached	
Residue 150µm AS 3799.3.1.6 (Method AS/NZS 2341.20)	Max. 0.2%	0.06%	

The sample submitted and identified by the client.

Steve Latham, File res, , File



Approved Signatory

V. Makhin

Date 9.11.2010 Serial No. 91026