

Technical Data Sheet

Evencure Hy-Cure

Two Coat Acrylic Curing Compound with Anti-Carbonation Properties

Description

Evencure Hy-Cure is a unique two coat acrylic emulsion curing system.

It has been formulated to achieve maximum curing efficiency as well as achieving a natural finish, anti-carbonation coating.

Application

To enable a good finish, it is imperative that the correct application method is followed.

It is recommended that Evencure Hy-Cure be applied by airless spray, pressure pot spray or traditional type spray gun. Evencure Hy-Cure can be applied by roller, but it is important to apply the correct rate per litre and NOT to apply material too thickly. Keep a wet edge to enable a continuous film.

APPLICATION RATE:-
Curing 5²m per litre per coat

IT IS HIGHLY RECOMMENDED THAT APPLICATORS TEST ANY EVENRANGE SYSTEM BEFORE APPLICATION TO ENSURE COMPABILITY AS EACH SURFACE PROFILE VARIES WITH INDIVIDUAL CONDITIONS.

FIRST COAT

North to South spraying style.

Apply the first coat of Evencure Hy-Cure to the surface as soon as the bleed water has disappeared at a rate of 5²m per litre.

KEEP AT 'WET EDGE' TO ENABLE A CONTINUOUS FILM

SECOND COAT

East to West spraying style

Allow a minimum of at least 20 minutes between coats. Apply the second coat in the opposite direction to the first coat at a rate of 5²m per litre.

AFTER TRADES

Evencure Hy-Cure requires a light scuff, prior to application of the after trade, to create a "key" to ensure adhesion between coatings.

Available in 20lt, 200lt and 1000lt containers.

Special Features

Due to its unique formulation Evencure Hy-Cure can be used as a "primer" coating. This allows after trades to be applied, including cementitious repairs materials, epoxies, anti-graffiti coatings etc., negating the need to remove curing compound before application.

Benefits

- Extremely high curing efficiency
- Ideal primer for most after trades
- Natural finish when cured
- Anti-carbonation properties
- Water-based system
- Ideally suited for precast concrete
- No waxes, resins, or solvents

Contact

EVENRANGE PTY LTD
12 Frankston Gardens Drive
CARRUM DOWNS. Vic 3201 Aust
Phone 03 9782 3233
www.evenrange.com.au
ABN 92 062 754 545